

Serial No.: 10/808,884

Filed: March 25, 2004

RECEIVED
CENTRAL FAX CENTER

OCT 24 2007

Complete set of claims:

1(withdrawn). A positive bottom photoimageable antireflective coating composition which is capable of being developed in an aqueous alkaline developer, wherein the antireflective coating composition comprises a water insoluble polymer comprising at least one recurring unit with a chromophore group and one recurring unit with a hydroxyl and/or a carboxyl group, a vinyl ether terminated crosslinking agent, a thermal acid generator and optionally, a photoacid generator.

2(withdrawn). The composition according to claim 1, wherein the chromophore group is chemically bonded to the polymer and is selected from a compound containing aromatic hydrocarbon rings, a substituted or unsubstituted phenyl group, a substituted or unsubstituted anthracyl group, a substituted or unsubstituted phenanthryl group, a substituted or unsubstituted naphthyl group, a substituted or an unsubstituted heterocyclic aromatic rings containing heteroatoms selected from oxygen, nitrogen, sulfur, and a mixture thereof.


3(withdrawn). The composition according to claim 1, wherein the recurring unit containing a hydroxyl and/or a carboxyl group is derived from a monomer selected from acrylic acid, methacrylic acid, vinyl alcohol, hydroxystyrenes, copolymers of hydroxystyrene and vinyl monomers containing 1,1,1,3,3,3-hexafluoro-2-propanol.

4(withdrawn). A positive bottom photoimageable antireflective coating composition which is capable of being developed in an aqueous alkaline developer, wherein the antireflective coating composition comprises a water

Serial No.: 10/808,884
Filed: March 25, 2004

insoluble polymer comprising at least one recurring unit with a chromophore group and a hydroxyl and/or a carboxyl group, a vinyl ether terminated crosslinking agent, a thermal acid generator and optionally, a photoacid generator.

5(withdrawn). The composition according to claim 1, where the vinyl ether terminated crosslinking agent is represented by the general structure below;



wherein, R is selected from a (C₁-C₃₀) linear, branched or cyclic alkyl, substituted or unsubstituted (C₆-C₄₀) aryl, and substituted or unsubstituted (C₇-C₄₀) alicyclic hydrocarbon; and n ≥ 2.

6(cancel).

7(withdrawn). The composition of claim 1, where the acid derived from the thermal acid generator has a pKa greater than 1.0.

8(withdrawn). The composition of claim 1, where the acid derived from the thermal acid generator is removed from the antireflective coating composition at temperatures below 220°C.

9(withdrawn). The composition according to claim 1 further comprising a dye.

10(withdrawn). The composition according to claim 9, wherein the dye is selected from the group consisting of a monomeric dye, a polymeric dye and a mixture of a monomeric and a polymeric dye.

Serial No.: 10/808,884
Filed: March 25, 2004

11(withdrawn). The composition according to claim 1, wherein the antireflective composition has a k value in the range of 0.1 to 1.0.

12(cancel).

13(withdrawn). The composition according to claim 1, wherein the photoacid generator is sensitive to actinic radiation in the range of 50 nm to 450 nm.

14(withdrawn). A process for forming a positive image comprising:

- a) forming a coating of the bottom photoimageable antireflective coating composition of claim 1 on a substrate;
- b) baking the antireflective coating,
- c) providing a coating of a top photoresist layer over the bottom coating;
- d) imagewise exposing the photoresist and bottom coating layers to actinic radiation of same wavelength;
- e) post-exposure baking the photoresist and bottom coating layers on the substrate; and,
- f) developing the photoresist and bottom coating layers in the same step with an aqueous alkaline solution.

15(withdrawn). The process according to claim 14, further comprising the step of removal of an edgebead after the coating and prior to the baking of the antireflective coating composition.

Serial No.: 10/808,884

Filed: March 25, 2004

16(withdrawn). The process according to claim 14, wherein the antireflective coating becomes insoluble in organic solvents and aqueous alkaline solution after the baking step prior to coating the photoresist layer and becomes soluble in aqueous alkaline solution after exposure to actinic radiation prior to developing the photoresist and bottom antireflective coating layer.

17(withdrawn). The composition according to claim 1, where the composition further comprises an acid.

18(withdrawn). The composition of claim 17, where the acid has a pKa greater than 1.0.

19(withdrawn). The composition of claim 17, where the acid is removed from the antireflective coating composition at temperatures below 220°C.

20(withdrawn). The composition according to claim 4, wherein the chromophore group is chemically bonded to the polymer and is selected from a compound containing aromatic hydrocarbon rings, a substituted or unsubstituted phenyl group, a substituted or unsubstituted anthracyl group, a substituted or unsubstituted phenanthryl group, a substituted or unsubstituted naphthyl group, a substituted or an unsubstituted heterocyclic aromatic rings containing heteroatoms selected from oxygen, nitrogen, sulfur, and a mixture thereof.

21(withdrawn). The composition of claim 4, where the chromophore group has a pendant hydroxyl and/or a carboxyl group, or the chromophore group and the hydroxyl and/or a carboxyl group are attached to the same group.

Serial No.: 10/808,884
Filed: March 25, 2004

22(previously presented). A positive bottom photoimageable antireflective coating composition which is capable of being developed in an aqueous alkaline developer, wherein the antireflective coating composition comprises a water insoluble polymer comprising at least one recurring unit with a chromophore group and one recurring unit with a hydroxyl and/or a carboxyl group, a vinyl ether terminated crosslinking agent, and optionally, a photoacid generator, further where the chromophore group is selected from a substituted or unsubstituted anthracyl group, a substituted or unsubstituted phenanthryl group, a substituted or unsubstituted naphthyl group, a substituted or an unsubstituted heterocyclic aromatic rings containing heteroatoms selected from oxygen, nitrogen, sulfur, and a mixture thereof.

23(previously presented). The composition according to claim 22, where the polymer comprises an ester of an anthracyl group and a phenolic group.

24(previously presented). The composition of claim 22, further comprising an acid.

25(previously presented). The composition according to claim 22, where the vinyl ether terminated crosslinking agent is represented by the general structure below;



wherein, R is selected from a (C₁-C₃₀) linear, branched or cyclic alkyl, substituted or unsubstituted (C₆-C₄₀) aryl, and substituted or unsubstituted (C₇-C₄₀) alicyclic hydrocarbon; and n ≥ 2.


Serial No.: 10/808,884
Filed: March 25, 2004

26(previously presented). The composition according to claim 22, wherein the photoacid generator is sensitive to actinic radiation in the range of 50 nm to 450 nm.

27(previously presented). A positive bottom photoimageable antireflective coating composition which is capable of being developed in an aqueous alkaline developer, wherein the antireflective coating composition comprises a water insoluble polymer comprising at least one recurring unit with a chromophore group and a hydroxyl and/or a carboxyl group, a vinyl ether terminated crosslinking agent, and optionally, a photoacid generator, further where the chromophore group is selected from a substituted or unsubstituted anthracyl group, a substituted or unsubstituted phenanthryl group, a substituted or unsubstituted naphthyl group, a substituted or an unsubstituted heterocyclic aromatic rings containing heteroatoms selected from oxygen, nitrogen, sulfur, and a mixture thereof.

28(previously presented). The composition of claim 27, further comprising an acid.

29(previously presented). The composition according to claim 27, where the vinyl ether terminated crosslinking agent is represented by the general structure below;



wherein, R is selected from a (C₁-C₃₀) linear, branched or cyclic alkyl, substituted or unsubstituted (C₆-C₄₀) aryl, and substituted or unsubstituted (C₇-C₄₀) alicyclic hydrocarbon; and n ≥ 2.

Serial No.: 10/808,884
Filed: March 25, 2004

30(previously presented). The composition according to claim 28, wherein the photoacid generator is sensitive to actinic radiation in the range of 50 nm to 450 nm.

Serial No.: 10/808,884
Filed: March 25, 2004

Respectfully submitted,



Sangya Jain
Reg. No. 38,504
AZ Electronic Materials USA Corp.
70, Meister Avenue,
Somerville, NJ 08876
Telephone: (908) 429-3536
Fax: (908) 429-3650

Customer No. 26,289